

# MARIAFLORA

ITALIAN LUXURY PERFORMANCE FABRICS

## SCRATCH 10566

Composition: 100% Trevira CS

Width: 131cm / 51"

Weight: 950 gr/m - 30 oz/yd

H rep: /

V rep: /

Martindale: 30.000

Light fastness: 6/7

Fire rating:

Mariaflora Trevira CS fabrics pass:

DIN 4102, DIM 4102-B1

EN 1021 – 1+2

BS 5852 CRIB5

IMO part 7


IMO part 8



Flame  
retardant



Crib 5



IMO



in-outdoor



water  
repellent



stain resistant

## Cleaning instructions:

Under normal conditions Mariaflora fabrics woven in Trevira can be hand-or machine-washed with a gentle 30°C (86°F) cycle and a soft detergent.

Low speed spin dry, then air dry.

Avoid using tumble dryers.

Trevira fabrics do not withstand the harshness of chlorine bleach or strong chemicals.

Professional dry cleaning is always recommended



For more information about Care and Maintenance please contact our Customer Service at [info@mffu.it](mailto:info@mffu.it).



## Approval of the Trademark Trevira CS®

Filippo Uecher S.r.l.  
Via Leonardo da Vinci, 5  
13854 QUAREGNA BI  
Italy

|  |  |
|--|--|
| <b>Application No.:</b>                    | 191222   |
| <b>Date of issue:</b>                      | 18.11.2019   |
| <b>Valid until:</b>                        | 18.11.2024   |
| <b>Article name:</b>                       | Violetta 10306   |
| <b>End use:</b>                            | Drapes<br>Upholstery fabrics<br>Wall coverings   |
| <b>Square weight (g/m<sup>2</sup>):</b>    | 450  |
| <b>According to customer specification</b> |  |
| <b>Composition of fabric:</b>              | Polyester 100% Trevira CS  |
| <b>Yarn:</b>                               | Warp, 2 / 10 Nm Trevira® Type Trevira CS,<br>Yarn supplier Tintoria Sala S.r.l.<br>Warp, 2 / 10 Nm Trevira® Type Trevira CS,<br>Yarn supplier Tintoria Sala S.r.l.<br>Weft, 17 / 2 Nm Trevira® Type Trevira CS,<br>Yarn supplier Fil Man Made Group S.r.l. |

The tested article Violetta 10306 with application no. 191222 is granted approval for the trademark Trevira CS® for interior use. This article was tested according to DIN 4102 part 1, 6.2 and thus also meets the requirements for fire class DIN 4102-B1.

The article was tested according to the French Standard NF P 92-504 (Propagation de flamme) and thus also meets the requirements for class M1 according to NF P 92-503, 92-505 and 92-507.

The article meets the requirements for class 1 according to EN 13773.

This article also meets the requirements for class I according to the North American standard NFPA 260 for upholstered furniture (based on the Test Reports no. 10-002-775 A + B dated 24.11.2010).

This article meets the requirements according to EN 1021 part 1+2 in conjunction with polyurethan foams with a density of more than 30 kg/m<sup>3</sup>.

Thus meets also the requirements according to British Standard BS 5867 part 2 type C.

Thus meets also the requirements according to British Standard BS 5852: ignition source 0 (cigarette), ignition source 1 (match) and ignition source 5 (crib 5) in conjunction with suitable combustion modified foams (at least 50 kg/m<sup>3</sup>).

Thus meets also the requirements for class 1 according to the Italian Standards UNI VF 8456 and UNI VF 8457.

Thus meets also the requirements according to the Italian standard UNI VF 9175, class 1 IM in conjunction with suitable combustion modified foams.

This article qualifies for class B-s1, d0 according to the European Standard EN 13501-1. Trevira CS has been approved by the DIBt with the General Building Inspectorate Approval, Approval No. Z-56.25-3573 dd. 24 April 2018.

Trevira GmbH  
(This document is valid without signature.)

Trevira GmbH, Trademark Service, Max-Fischer-Straße 11, 86399 Bobingen, Germany  
E-Mail: [trademark.service@trevira.com](mailto:trademark.service@trevira.com)